

Facestock

An extremely tough, clay-coated white kraft paper, siliconized and with low release.

Basis Weight	80.00000 g/m ²	ISO 536
Caliper	82 µm	ISO 534
Tear Strength MD	>4.6 KJ/m ²	DIN EN ISO 1924-2
Tear str. CD	>440 mN	ISO 1974
Release level	20 cN/20mm	PTS method - K7476 / 40°C

Applications and Use

This material is moisture stabilized and thus has got a very good dimensional stability. It is particularly suitable for self-adhesive products in sheets.

Conversion and Printing

Specially designed for high speed conversion, punching and perforation.

Shelf Life

To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

BO871

Fasson ®

LINER HF80WH LR FSC



LINER HF80WH LR FSC



The mark of
responsible forestry

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2024 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.