



PRODUCT PAGE



Material:	Nomex 414
------------------	------------------

Overview:

NOMEX Type 414 has similar electrical and thermal stability property of NOMEX 410 but with more flexible and conformable sheet with open surface. It is available thicknesses ranging from 0.18 mm (7 mil) to 0.38 mm (15 mil), with specific gravity ranging from 0.9 to 1.0. With excellent features of long term operating high temperature at 220° and inherent dielectric strength, Nomex 414 is ideally for the use as slot insulation in hand-wound motors, linear wrapping of wire, as well as main insulation for dry-type transformers where conformability and impregnability are required. It can be also laminated with 3M adhesive tapes like 3M 467, 3M9460PC etc, and then die cut into small parts to provide immediate usage in various of application.

Description:

Parameters:

Characteristics	Units	Value	Test Method
Series		414	
Application use		Insulation	
Shape		Roll	
Thickness		0.25	
Operation temperatures		- 220	
Dielectric Strength	V/mil	710	ASTM D149
Full Wave Impulse	V/mil	1300	ASTM D3426
Dielectric Constant at 60 Hz		2.7	ASTM D150
Dissipation Factor at 60 Hz (x 10 ⁻³)		8	ASTM D150

Warranty:**Technical data**

All information and statements contained in this document are based on the manufacturer's or material supplier's sources known to us at the time of filing. PERLON, spol. s r.o. believes them to be reliable in good faith, but the accuracy and/or completeness of such information is not guaranteed. The data should be considered representative or typical only and should not be used for specification purposes. Manufacturers reserve the right to make changes to the design, construction and technical data of products without prior notice.

Use of the product

Many factors beyond the control of PERLON, spol. s r.o. and known only to the user may affect the use and performance of materials in a particular application. Therefore, we recommend that the customer perform their own tests of the suitability and performance of the material for their application and to a responsible extent for reliable results. As a result, the customer is solely responsible for evaluating the product and determining if it is suitable for the customer's application, including evaluating workplace hazards and reviewing all applicable regulations and standards. Failure to properly evaluate, use, or comply with all applicable safety regulations may result in injury, illness, death, and/or property damage if the material and associated safety is not properly evaluated. PERLON, spol. s r.o. makes no warranties of fitness for a particular purpose.

Limitation of liability

PERLON, spol. s r.o. shall not be liable for any loss or damage arising out of or relating to the product material, whether direct, indirect, special, incidental or consequential (including, but not limited to, loss of products or business), regardless of the applicable legal practice, including but not limited to warranty, contract, negligence or strict liability.

www.convertimg.sk